

# POWERCLEAN® II

## Spacer System

## Product Specifications



### DESCRIPTION

The POWERCLEAN® II spacer is a proprietary temperature-stabilized one-sack cementing system engineered to achieve required fluid properties for optimized displacement.

#### ADVANTAGE

Versatility in any well condition

Stable rheology at elevated temperatures

Compatible with all standard weighting materials

Can be mixed on the fly through the cement mixing system

Easily mixed in a batch mixer, displacement tanks or on the fly

#### APPLICATION

Boosts drilling fluid displacement

Separates the drilling fluid and cement

Successful in washed-out wellbores

Enhances zonal isolation

### DESIGN RECOMMENDATION

Mix using rig hopper, batch mixer, or through cement mixing system

Mix water should be treated to remove high calcium or magnesium levels

For optimum rheology maintain a spacer pH of 9-10 with addition of OH ions or a pH buffer

When batch mixing, shear for 30 minutes after POWERCLEAN II is added. When a weighted spacer is required, shear an additional five minutes after weighting agents are added.

Add the surfactant or solvent last, if required for OBM/SBM water wetting to minimize foaming.

### PHYSICAL PROPERTIES

Appearance: Light grey powder

Specific gravity: 2.3–2.5 g/cm<sup>3</sup>

19.2–20.8 lb/gal

### HANDLING AND STORAGE

POWERCLEAN II spacer can be slippery when wet. Avoid breathing dust. Use POWERCLEAN II spacer only with adequate ventilation to keep exposures (airborne levels of dust, fume, vapor) below recommended limits. An approved dust mask should be worn if dust is generated during handling. Avoid build-up of dust. Keep containers in a clean, cool and dry area away from heat sources. Keep containers properly sealed when not in use. Review the SDS before using this product.

### PACKAGING

POWERCLEAN II spacer is available in 45-lb multi-walled bags. In total, 55 bags to a pallet.